

Seal Compatibility Chart

Seal Type	VP 700PM	VP 800PM	VP 805PM	VP 690M	VP-TechPM	VP 920PM
Natural Rubber (NR)	P	P	P	PCS	P	P
Latex	P	P	P	PCS	P	P
Isoprene Rubber (IR)	P	P	P	PCS	P	P
Styrene/Butadiene (SBR)	P	P	P	P	P	P
Mid-ACN Nitrile Buna N	G	G	G	G	G	G
High-ACN Nitrile Buna N	E	E	E	E	E	E
EPR	F	F	F	F	F	F
EPDM	F	F	F	F	F	F
Ethylene-Propylene Rubber	F	F	F	F	F	F
Nylon	G	G	G	G	G	G
Neoprene	F	F	F	G	F	PCB
Butyl (IIR)	P	P	P	PCS	P	F
Polysulfide Rubber	F	F	F	G	F	F
Urethane	P	P	P	F	P	P
Silicone	G	G	G	G	G	G
Fluorinated	G	G	G	G	G	G
Polyacrylate	P	P	P	G	P	P
PTFE (Teflon)	E	E	E	E	E	E
Vitron	E	E	E	E	E	E
Flurocarbon (FPM) Rubber	E	E	E	E	E	E
Fluorel Kel-F	E	E	E	E	E	E

E – Excellent

G – Good

F – Fair

P – Poor

PCS – Poor Causes Swelling

PCB – Poor Causes Brittleness

While this data and information is typical and conforms to quality specifications, variations might occur. The information in this document is not taken as an implied warranty for which ValCOOL assumes legal responsibility. ValCOOL assumes no liability for any alleged ineffectiveness of the product or any injury or damage, direct or consequential, resulting from the use of these products.